



**CORONADO**  
P A I N T

**SECTION NO.13**  
**ADS – 1401**  
**55-145**  
**Rev. 02/10**

**Super Kote 5000™**  
**Chrome Brite All Purpose Aluminum**  
**55-145**

Type	Sheen	Theoretical Spread Rate	Recommended Application	Thinner	Clean Up
Linseed Oil/Alkyd	Gloss	400 - 500 Sq. Ft. Per Gallon*	Brush, Roller or Spray	Mineral Spirits	Mineral Spirits
<b>Drying Schedule:</b>		<b>Tack Free:</b> 2 – 4 Hours	<b>Recoat:</b> 24 Hours	<b>Full Cure:</b> 10 Days	

<b>PRODUCT NAME:</b> 55-145 Super Kote 5000™ Chrome Brite All Purpose Aluminum	This Super Kote 5000™ Chrome Brite Aluminum Paint is designed to meet the stringent durability requirements of the industrial maintenance market while retaining the qualities so necessary to the amateur painter...ease of application, excellent adhesion with minimum surface preparation, easy clean up, excellent leveling and bright finish.	
<b>WHERE TO USE:</b>	<b>SUBSTRATES:</b>	<b>APPLICATIONS:</b>
	Wood Drywall Brick	Metal Concrete Masonry
On interior or exterior fences, tanks, roofs, equipment, pipes, support steel, bridges and elevated structures.		

<b>REGULATORY INFORMATION:</b>	<b>VOC/VOS STATEMENT:</b>	<b>OTC CATEGORY:</b>	<b>MPI / LEED:</b>
	The product supported by this data sheet contains a maximum of 470 grams per liter VOC / VOS (3.92 lbs/gal.) excluding water & exempt solvents.	This product is compliant under the Ozone Transport Commission regulations as a Metallic Pigmented Coating.	This product is certified under MPI #1. This product does not meet qualifications for LEED (Leadership in Energy and Environmental Design) projects.

<b>SURFACE PREPARATION:</b>	<p>Surface to be painted must be clean and free of dirt, chalk, wax, grease, rust or loose flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Wax should be removed with a commercial wax stripper or by solvent cleaning. Grease should be cleaned by using CORONADO® Sur-Prep™ I. Rust must be removed by hand sanding or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.</p> <p><b>PRIMING- (New or Bare Surfaces):</b>  <b>Plaster/Drywall</b> – For best results use CORONADO® Primer Sealer 40-11 or 78-11  <b>Wood</b> – Use CORONADO® Undercoat 37-11 or 78-11  <b>Masonry</b> – Use CORONADO® Masonry Sealer 48-11  <b>Ferrous Metal</b> – Use CORONADO® Metal Primers 35-111 or 36-11  <b>Non-Ferrous Metal</b> – Use Perma Bond 100-10  <b>Galvanized</b> – Use Perma Bond 100-10 or Grip &amp; Seal™ 116-11</p>
<b>APPLICATION:</b>	<p>Chrome Brite Aluminum may be brushed, rolled or sprayed. Best rolling results are obtained with a short nap mohair type roller. When brushing and rolling, flow material on with a minimum of strokes. Stir thoroughly before and periodically during use. Thinning is not recommended. Apply only when surface or air temperatures are between 40° and 90° F.</p> <p><b>Clean Up Note: Danger!</b> – Rags, Steel Wool or Waste soaked with linseed oil may spontaneously catch fire if improperly discarded. Immediately after use, place rags, steel wool or waste in a sealed water-filled metal container.</p>
<b>* NOTE ON SPREAD RATE:</b>	Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.

**SECTION NO.13**  
**ADS – 1401**  
**55-145**

<b>THINNING:</b>	This product is formulated to be applied as packaged and no thinning should be needed. If local VOC regulations / restrictions allow, this product can be thinned sparingly with mineral spirits.	
<b>RESIN TYPE:</b>	Linseed Oil/Alkyd	
<b>SOLIDS:</b>	Weight: 49.9 ± 1.0% Volume: 40.9 ± 1.0%	
<b>WEIGHT PER GALLON:</b>	7.7 lbs per gallon	
<b>VISCOSITY:</b>	53 – 60 KU (Krebs Units)	
<b>FLASH POINT:</b>	50° F. (TT-P-141, Method 4293)	
<b>SPECULAR GLOSS:</b>	80+ units @ 60 Degrees	
<b>SAG RATING:</b>	Pass 6 mils (Leneta)	
<b>REC. FILM THICKNESS:</b>	Wet:	3.2 to 4.0 mils
	Dry:	1.3 to 1.6 mils
<b>PERFORMANCE TESTING RESULTS:</b>	Meets the performance requirements of TT-P-38 Meets the performance requirements of SSPC Paint Specification 101 & 108	
<b>GENERAL CAUTIONS:</b>	<p style="text-align: center;"><b>DANGER!</b></p> <p>FLAMMABLE LIQUID AND VAPOR. HARMFUL OR FATAL IF SWALLOWED. Causes nose, throat, eye &amp; skin irritation. <b>NOTICE:</b> Reports have associated repeated and prolonged occupational overexposure to solvent with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. <b>Contains</b> VM&amp;P Naptha, Mineral Spirits and Lt. Aromatic Solvent, Naphtha. Keep away from heat, sparks and flame. Vapors can cause flash fire. Do not smoke. Extinguish all flames and pilot lights, and turn off stoves, heaters, electric motors and other sources of ignition during use and until all vapors are gone. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation.</p> <p><b>Use only with adequate ventilation.</b> Do not breathe dust, vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow manufacturer's directions for respirator use. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling.</p> <p><b>First Aid:</b> In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. If swallowed, do not induce vomiting. Get medical attention immediately.</p> <p>If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p><b>DANGER</b> – Rags, steel wool or waste soaked with this product may spontaneously catch fire if improperly discarded. Immediately after use, place rags, steel wool or waste in a sealed, water-filled metal container.</p> <p style="text-align: center;"><b>Obtain and read the MSDS prior to using this product.</b>  <b>KEEP OUT OF REACH OF CHILDREN</b></p>	