



CORONADO
P A I N T

SECTION NO.12
ADS – 1300
58 Line
Rev. 10/11

Super Kote 5000™
Latex Field Marking Paint
58 Line

Type Latex	Sheen Flat	Theoretical Spread Rate 3" Line - 400 Ft.* 4" Line – 300 Ft.* 5" Line – 240 Ft.* 6" Line – 200 Ft.*	Recommended Application Brush, Roller or Spray	Thinner Clean Water	Clean Up Warm Soapy Water
Dry Time:		Tack Free: 1 Hour	Recoat: 4 Hours	Full Cure: 7 Days	

PRODUCT NAME: 58 Line Super Kote 5000™ Latex Field Marking Paint	Super Kote 5000™ Latex Field Marking Paint is specifically designed for use on natural or artificial turf, concrete and asphalt, as a semi-permanent coating for line marking or artistic graphics.	
WHERE TO USE:	Natural Turf Artificial Turf Concrete Asphalt	On interior or exterior surfaces such as athletic fields or other areas requiring a semi-permanent marking.

REGULATORY INFORMATION:	VOC/VOS STATEMENT:	OTC CATEGORY:	MPI / LEED:
	The products supported by this data sheet contain a maximum of 30 grams per liter VOC / VOS (0.25 lbs/gal.) excluding water & exempt solvents.	This product is compliant under the Ozone Transport Commission regulations as a Flat Coating.	This product is not currently certified under MPI. This product does meet qualifications for LEED (Leadership in Energy and Environmental Design) projects as a Flat Coating.

SURFACE PREPARATION:	Surface to be marked must be dry and free of dust, grease, wax and other contamination that could affect adhesion. For best results, grass should be cut short.	
APPLICATION:	Super Kote 5000™ Field Marking Paint may be brushed, rolled, or sprayed (conventional or airless) or applied with gravity feed line marker. Do not apply when surface or air temperatures are below 50 degrees Fahrenheit. Do not apply to a hot surface. Thin with one quart of water per gallon when applying with spray or gravity feed marker.	
*NOTE ON SPREAD RATE:	Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.	
RESIN TYPE:	Vinyl Acetate/Acrylic	
SOLIDS:	Weight: 38.5 ± 1.0%	Volume: 22.3 ± 1.0%
WEIGHT PER GALLON:	10.5 lbs.	
VISCOSITY:	White: 110 – 115 KU (Krebs Units)	Yellow: 75-85 KU
FLASH POINT:	200° F. or greater (TT-P-141, Method 4293)	
SPECULAR GLOSS:	1 – 3 units @ 85 degrees	
SAG RATING:	N/A	
REC. FILM THICKNESS:	Wet:	4.0 to 8.0 mils
	Dry:	0.9 to 1.8 mils

CAUTIONS:	<p style="text-align: center;">CAUTION!</p> <p style="text-align: center;">Use only with adequate ventilation.</p> <p>Ensure fresh air during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow manufacturer's directions for respirator use.</p> <p style="text-align: center;">Contains Crystalline Silica</p> <p>First Aid: In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed, get medical attention immediately.</p> <p>If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p>WARNING: This product contains chemicals known to the state of California to cause cancer, birth defects or other reproductive harm.</p> <p style="text-align: center;">Obtain and read the MSDS prior to using this product.</p> <p style="text-align: center;">KEEP OUT OF REACH OF CHILDREN</p>
------------------	---