



TAB #12
Hot Trax™
Latex Satin Concrete
and Garage Floor Paint
HTF-XXX Series
 Rev. 10/09

Hot Trax™ Latex Satin Concrete and Garage Floor Paint HTF-XXX Series

Type	Sheen	Theoretical Spread Rate	Recommended Application	Thinner	Clean Up
Acrylic	Eggshell	300 - 400 Sq. Ft. Per Gallon*	Brush or Roller	Water	Warm Soapy Water
Dry Time:		Tack Free: 2 - 4 Hr.	Recoat: 24 Hrs.	Full Cure: 7 Days	

PRODUCT NAME: HTF-XXX Series Hot Trax™ Latex Satin Concrete and Garage Floor Paint	Hot Trax™ Latex Satin Concrete and Garage Floor Paint is a high performance, ready to use, water-based floor coating that resists hot tire pick-up and marring common to driveways and garage floors. This finish is extremely resistant to chemicals, water, oil and gasoline. Hot Trax is also ideal for use on exterior concrete, masonry, stucco, cinder block and brick. This durable finish is resistant to cracking.		
WHERE TO USE:	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 15%; text-align: center;">Interior & Exterior</td> <td>Concrete floors, walkways, patios and pavers. Also can be used on masonry, stucco, block and brick.</td> </tr> </table>	Interior & Exterior	Concrete floors, walkways, patios and pavers. Also can be used on masonry, stucco, block and brick.
Interior & Exterior	Concrete floors, walkways, patios and pavers. Also can be used on masonry, stucco, block and brick.		
SURFACE PREPARATION:	<p>Proper surface preparation is essential for adhesion of the paint. All surfaces must be clean, sound, dry and free of any dirt, dust, oil, wax or grease. Fill all holes and cracks with suitable patching compound or caulk.</p> <p>New or Unpainted Surfaces: Poured or precast concrete must cure for 60 days and then must be acid etched using a commercial acid etch product. (Follow all directions for acid etching.) Rinse thoroughly and allow to dry. Using a stiff bristle broom, thoroughly sweep and/or vacuum all residue left from etching process. If floor is porous, prime with this material thinned with 1 pint of clean water per gallon.</p> <p>Old Weathered or Previously Painted Surfaces: Remove all loose peeling paint from previously painted surface. Wash off all dirt, grease, wax, oil and soap with a high quality concrete floor cleaner. Powerwash exterior floors to remove any chalking. Rinse and allow to dry. Lightly sand previous paints that are smooth or glossy. Prime bare areas as listed under new surfaces.</p> <p>SPECIAL NOTE: To help avoid premature paint failure, additional cleaning should be given to all concrete floors that have been previously exposed to automobile tires.</p>		
APPLICATION:	<p>Hot Trax™ applies easily with a quality brush or roller. This product is not designed for spray application.</p> <p>Stir product thoroughly before using. It is important to maintain a wet edge during all methods of paint application by brushing or rolling into previously applied coating area. Surface should be thoroughly dry before applying paint. When working with more than one container of the same color, intermix to ensure color uniformity. Stir paint before and occasionally during application. Do not apply at a surface or air temperature below 50°F. Avoid applying paint in direct sunlight or to hot surfaces. Do not paint if surface temperature is within 5° F of the dew point.</p> <p>Provide good ventilation for normal drying. Apply a thin even coat using 3/8" nap roller cover or a nylon/polyester brush. Allow the first coat to dry 24 hours before applying a second coat. Apply the second coat in a cross direction of the first coat to achieve uniform coverage.</p> <p style="text-align: center;">KEEP FROM FREEZING.</p>		

TAB #12
Hot Trax™
Latex Satin Concrete
and Garage Floor Paint
HTF-XXX Series
Rev. 10/09

*NOTE ON SPREAD RATE:	Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.
TINTABILITY:	Hot Trax™ is available in Silver Gray, Light Gray, Tile Red and Hunter Green. It is also available in a Tintable White and an Accent Tint Base. It can be tinted with 888 Universal colorants (up to 2 oz/gal in the White and up to 12 oz/gal in the Accent Tint Base).
RESIN TYPE:	Acrylic
SOLIDS:	Weight – 42.7 ± 1.0% Volume – 28.6 ± 1.0%
WEIGHT PER GALLON:	10.4 lbs.
VISCOSITY:	90 – 95 KU (Krebs Units)
FLASH POINT:	200° F or greater (TT-P-141, Method 4293)
SPECULAR GLOSS:	5 - 10 units @ 60 degrees
REC. FILM THICKNESS:	Wet: 4.0 to 5.3 mils Dry: 1.1 to 1.5 mils
CAUTIONS:	<p style="text-align: center;">CAUTION Use only with adequate ventilation.</p> <p>Ensure fresh air during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use.</p> <p>First Aid: In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed, get medical attention immediately.</p> <p>If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p style="text-align: center;">Obtain and read the MSDS prior to using this product. KEEP OUT OF REACH OF CHILDREN</p>
VOC/VOS STATEMENT:	This product contains a maximum of 200 grams VOC/VOS per liter of coating. (1.67 pounds per gallon).
OTC CATEGORY:	This product is compliant under the Ozone Transport Commission regulations as a Floor Coating.