



Chlorinated Rubber Swimming Pool Paint

CR-2600 Series

| | | | |
|------------------------------|--|---------------------|-------------------|
| PRODUCT NAME: | Chlorinated Rubber Swimming Pool Paint | | |
| PRODUCT NUMBERS: | CR-2600 Series | | |
| DESCRIPTION: | A chlorinated rubber base coating for new or old concrete pools. Durable in fresh or salt water. Resists fading, fungus, algae, abrasion and alkalis. See <i>Insl-x Swimming Pool Paint Brochure for complete instructions regarding application.</i> | | |
| SUGGESTED USES: | Concrete, Gunnite*, Marcite*, Pools <i>*Integrity of marcite or gunnite must be sound and solid.</i> | | |
| COLORS: | Ocean Blue Off White | Aquamarine Black | Royal Blue Red |
| FINISH: | Semi-Gloss | | |
| VEHICLE TYPE: | Chlorinated Rubber | | |
| SOLVENT TYPE: | Aromatic and Aliphatic Hydrocarbons | | |
| VOC: | 4.76 #/gal (571 g/l) white | | |
| WET HEAT RESISTANCE: | 95°F maximum | | |
| FLASH POINT: | 54°F Seta Flash | | |
| SOLIDS BY VOLUME: | 33.2% | | |
| WEIGHT PER GALLON: | 11.5 lbs. | | |
| RECOMMENDED DRY FILM: | 2 mils per coat. Apply a minimum of 2 coats on new surfaces | | |
| COVERAGE: | Theoretical coverage is 266 square feet per gallon at two mils dry. Material losses during mixing and application will vary and must be taken into consideration when estimating job requirements. | | |
| VISCOSITY: | 70-80 KU | | |
| RECOMMENDED DRY TIME: | Set to touch in 30 minutes, Re-coat in 24 hours | | |
| REDUCER: | TH-0208. Do not thin if doing so would result in exceeding VOC limitations. | | |
| CLEAN UP: | TH-0208 | | |
| PHYSICAL PROPERTIES: | Resists Mildew, Algae, Fresh & Salt Water, Suntan Oils. | | |
| RECOMMENDED PRIMERS: | Self Priming | | |
| APPLICATION: | Brush, Roller, or Spray Roll: 3/8" lambs wool or 1/4" -3/8' synthetic roller cover. Keep roller wet. Roll in one direction, rewet, then cross roll. | | |

